




BASIC 5%



blanco
white
300-5% **12352916**
250-5% **12351916**
200-5% **12350916**



nevawhite
nevawhite
300-5% **12352900**



blanco puro
pure white
300-5% **12352910**
250-5% **12351910**
200-5% **12350910**



blanco/lino
white / linen
300-5% **12352991**
250-5% **12351991**
200-5% **12350991**




beige
beige
300-5% **12352115**



blanco/gris
white grey
300-5% **12352992**
250-5% **12351992**
200-5% **12350992**



gris medio
medium gray
300-5% **12352740**
250-5% **12351740**
200-5% **12350740**



grafito
graphite
300-5% **12352715**



negro
black
300-5% **12352911**

Características técnicas	Technical characteristic	Caractéristiques technique	Caratteristiche tecnica	Características técnicas	خصائص تقنية
Peso / Weight / Poids / Peso / Peso / وزن	410 g/m² ± 10 %			Resistencia a la tensión Tensile strength Résistance à la traction Resistência ao tração Resistenza alla trazione قوة الشد	Urdimbre / Warp Chaîne / Urdidura Trama / Weft Trame / Trama 160 daN/5 cm 150 daN/5 cm DIN53354:1981
Ancho / Width / Largeur Largura / Larghezza / عرض	200-250-300 cm Ver muestras			Resistencia al rasgado Tearing strength Résistance à la déchirure Resistência ao rasgamento Resistenza allo strappo مقاومة التمزق	Urdimbre / Warp Chaîne / Urdidura Trama / Weft Trame / Trama 34,6 daN 30,4 daN DIN53363:2003
Espesor / Thickness / Épaisseur Espessura / Spessore / سماكة	0,55 mm ± 0,05			Medio ambiente / Environment Environnement / Medio ambiente Ambiente / بيئة	OEKO-TEX 100 GREENGUARD
Largo del rollo / Roll length / Longueur du rouleau Comprimento do rolo / Lunghezza del rotolo / طول اللفة	30 m ± 5 %			Resistencia a la luz / Light fastness Résistance à la lumière / Resistência à luz Resistenza alla luce / مقاومة الضوء	AATCC 16-2003 Class 4.5 After 80 AFU
Composición / Composition / Composition Composição / Composizione / التركيبة	70% PVC 30% polyester			Resistente al fuego / Fire resistance Résistance au feu / Resistência ao fogo Resistente al fuoco / مقاوم النار	
Factor de Apertura / Openness Factor Facteur d'ouverture / Fator de Abertura Fattore di apertura / عامل الانفتاح	5%			UV-A Factor	95 %
Urdimbre / Warp / Chaîne / Urdidura / Ordito Trama / Weft / Trame / Trama / Trama	48				
	46				