


BLACKOUT




beige: tras. blanca
beige: white back

300 **12202905**
244 **12209905**
183 **12212905**



blanco
white

300 **12202900**
244 **12209900**
183 **12212900**



marfil
ivory

300 **12202113**
183 **12212113**




perla
pearl

300 **12202010**
244 **12209010**
183 **12212010**




beige
beige

300 **12202938**
244 **12209938**
183 **12212938**



gris
gray

300 **12202868**
244 **12209868**
183 **12212868**



gris oscuro
dark gray

300 **12202743**
244 **12209743**
183 **12212743**



negro
black

300 **12202964**
244 **12209964**
183 **12212964**

Características técnicas Technical characteristic Caractéristiques technique Caratteristiche tecniche Características técnicas خصائص تقنية

Peso / Weight / Poids / Peso / Peso / وزن	537 g/m² ±5 %
Ancho / Width / Largeur Largura / Larghezza / عرض	182-244-300 cm ver muestras
Espesor / Thickness / Épaisseur Espessura / Spessore / سماكة	0,29 mm ±5 %
Largo del rollo / Roll length / Longueur du rouleau Comprimento do rolo / Lunghezza del rotolo / طول اللفة	25 m ±10 %
Composición / Composition / Composition Composição / Composizione / التركيبة	75 % PVC 25 % fiberglass
Resistente al fuego / Fire resistance Résistance au feu / Resistência ao fogo Resistente al fuoco / مقاوم النار	FR NFPA701:2010
Resistencia a la luz / Light fastness Résistance à la lumière / Resistência à luz Resistenza alla luce / مقاومة الضوء	AATCC 16-2003 Class 4.5 After 80 AFU
Termosoldable / Thermo welding allowed / Thermoscellable Termosselável / Saldabile / قابل للحام	

Imprimible / Printable / Imprimabile Imprimível / Stampabile	HP Latex printer tested
Limpiar con un trapo húmedo / Wet wipe Nettoyer avec un chiffon humide / Limpe com um pano húmido التنظيف باستخدام قطعة قماش مبللة / Pullire con un panno umido	
Temperaturas mínima y máxima de uso para mantener la estabilidad del producto. Minimum and maximum temperatures of use of the product to maintain its stability. Températures minimale et maximale d'utilisation du produit pour maintenir sa stabilité. Temperaturas mínima e máxima de uso do produto para manter sua estabilidade.	-10 °C + 60 °C
La no utilización de cristales con protección ultravioleta puede deformar el producto, en mayor medida si están orientados al sur. The non-use of glass with ultraviolet protection can deform the product, especially if they are oriented to the south. La non utilisation de verre avec protection contre les rayons ultraviolets peut déformer le produit, surtout s'ils sont orientés vers le sud. O não uso de vidro com proteção ultravioleta pode deformar o produto, especialmente se forem orientados para o sul.	