

SUPREME



blanco
white
250-3% **12257001**



beige
beige
250-3% **12257002**



pardo
brown
250-3% **12257013**



chocolate
chocolate
250-3% **12257508**



gris claro
light grey
250-3% **12257003**



gris medio
medium gray
250-3% **12257012**



negro
black
250-3% **12257507**

Características técnicas	Technical characteristic	Caractéristiques technique	Caratteristiche tecnici	Características técnicas	خصائص تقنية
Peso / Weight / Poids / Peso / Peso / وزن	520 g/m² ± 10 %		Resistencia a la tensión Tensile strength Résistance à la traction Resistência à tração Resistenza alla trazione قوة الشد	Urdimbre / Warp Chaîne / Urdidura Trama / Weft Trame / Trama	252 daN/5 cm 228 daN/5 cm DIN53354:1981
Ancho / Width / Largeur Largura / Larghezza / عرض	250 cm		Resistencia al rasgado Tearing strength Résistance à la déchirure Resistência ao rasgamento Resistenza allo strappo مقاومة التمزق	Urdimbre / Warp Chaîne / Urdidura Trama / Weft Trame / Trama	34,6 daN 30,4 daN DIN53363:2003
Espesor / Thickness / Épaisseur Espessura / Spessore / سماكة	0,72 mm ± 0,05		Resistencia a la luz / Light fastness Résistance à la lumière / Resistência à luz Resistenza alla luce / مقاومة الضوء		AATCC 16-2003 Class 4.5 After 80 AFU
Largo del rollo / Roll length / Longueur du rouleau Comprimento do rolo / Lunghezza del rotolo / طول اللفة	27,4 m ± 5 %		UV-B Factor UV-A Factor Ultraviolet Protection Factor		94,9 % 97,2 % UPF 15 AITEK STANDARD 801 2019-AN2034
Composición / Composition / Composition Composição / Composizione / التركيبة	73% PVC 27% polyester				
Resistente al fuego / Fire resistance Résistance au feu / Resistência ao fogo Resistente al fuoco / مقاوم النار	FR NFPA701(USA) M2 NFP92-503 B2 GB 50222-95				
Factor de Apertura / Openness Factor Facteur d'ouverture / Fator de Abertura Fattore di apertura / عامل الانفتاح	3%				
Urdimbre / Warp / Chaîne / Urdidura / Ordito Trama / Weft / Trame / Trama / Trama	36 28				
Soldable con Ultrasonido / Ultrasonic welding allowed / Soudable avec ultrasons / Soldável com ultra-som / Saldabile con ultrasuoni					



Uso en interiores y exteriores
Indoor and outdoor use
Utilisation intérieure et extérieure

Uso indoor e ao ar livre
Uso interno ed esterno